

Comparative Study of Concrete with Different Fiber with and without Fly Ash as Admixture

Jai Kumar Kushwaha¹, Prof. Shikha Shrivastava²

¹M Tech Student, ²Assistant Prof.

^{1,2}Department of Civil Engineering, SIET, Jabalpur

Abstract - The effect of addition of mono fibers and hybrid fibers on the mechanical properties of concrete mixture is studied in the present investigation. Besides cubes and beams of M30 grade concrete were cast with 25 and 30 % of fly ash and different percentages of steel fiber and polypropylene fiber and hybrid fibers respectively, by volume of cement and identifies fiber combinations that demonstrate maximum compressive and flexural strength of concrete. Finally we obtained that by addition of fiber and mineral admixture the concrete increase their properties as compare to normal concrete mass. Super plasticizer was also used in all mixes to make concrete better in workability.

Keywords - Fibrous Concrete, Hybridization, Polypropylene Fiber, Steel Fiber, Hybrid Fabric, Orthodoxy- Fiber, Strength Properties, Fly-Ash.

I. INTRODUCTION

To improve the pre cracking and post cracking behavior of concrete short discontinuous and discrete fibers are added to the plain concrete to make it fibrous concrete [1]. The infrastructure needs of our country is increasing day by day and with concrete is a main constituent of construction material in a significant portion of this infra-structural system, it is necessary to enhance its characteristics by means of strength and durability [2]. Concrete is a relatively brittle material. Addition of fibers to concrete makes it a more ductile material [3]. It is obvious that the behavior of HFRC depends on the aspect ratios, orientations, geometrical shapes, distributions and mechanical properties of fibers in concrete mixtures. From a brittle to a more ductile material [4].

II. MATERIALS AND METHODS

In this study, materials used are ordinary Portland cement, fine aggregate, coarse aggregate, steel fibers, polypropylene fibers and fly ash. The Ordinary Portland cement of 43 grade confirming to IS 8112-1989 manufactured by Ultra Tech Company was used in this experimental work [5]. Cement with specific gravity 3.12 was used for the preparation of test specimens [6]. There are different type of cement; out of that have used 43 grade ordinary Portland cement (OPC). Initial and Final setting time of cement respectively is 90 min and 360 min. Broken stone from the local quarry of size 20 mm and 10 mm in the ratio of 60:40 respectively confirming to IS: 383-1970

has been used as coarse aggregate [7]. The specific gravity of 10 mm and 20 mm coarse aggregate were taken as 2.72 and 2.74 respectively. Water absorption for 10 mm and 20 mm aggregate were 0.17 and 0.15 % respectively. Fineness modulus of 10 mm and 20 mm were 2.31 and 2.65 respectively [8]. Locally available river sand of zone II conforming to IS 383-1970 with specific gravity 2.69, water absorption 1.82 % and fineness modulus 2.86 [14]. Clean and portable water from tap was used for mixing of concrete and curing the concrete as per IS: 456-2000 in the entire experimental program [9]. Fly ash is one of the most extensively used by-product materials in the construction field resembling Portland cement. It is an inorganic, non-combustible, finely divided residue collected or precipitated from the exhaust gases of any industrial furnace [10]. Steel fibers with Hooked end & Flat crimped were used in the mixes. The steel fibers had a length of 50 mm and a diameter of 0.75mm (an aspect ratio of 100). The density of the fibers was 7.65 g/cm³ and the young's modulus was 210 GPa. Fibrillated 20 mm cut length fibers were used. Polypropylene fiber had a length of 20 mm and a diameter of 1mm (an aspect ratio of 100) [12]. The specific gravity of polypropylene fiber is 0.9[12]. Super plasticizer was also used in all mixes to make concrete better in workability [11].

Following test were conducted on prepared samples as per relevant IS code [15].

Slump cone Test - The slump test is prescribed by IS: 456 (2000), ASTM C 143 90A and BS 1881 Part 102:1983. This is a test used extensively in site work all over the work [13].

Compressive Strength Test - Test for compressive strength is carried out either on cube or cylinder. Out of many test applied to the concrete, this is the utmost important which gives an idea about all the characteristics of concrete. By this single test one judge that whether Concreting has been done properly or not [16].


Flexural Strength Test - The flexural strength of concrete prism was determined based on IS: 516 –1959. Beam specimens of size 100 mm x 100 mm x 500 mm were casted. The samples were de-molded after 24 h from casting and kept in a water tank for 7 days and 28 days

curing. The specimens were placed in UTM and tested for flexural strength [17].


The mix proportion of 1: 1.73: 2.72 using I.S. code method with water cement ratio .45 to get a characteristic strength of M30, was considered for this study. The parameters varied were fiber content vary 0-4% as additives and fly ash 25 to 30 % by weight of cement. The cement, fine aggregate, coarse aggregate, steel fiber and fly ash were tested prior to the experiments and checked for conformity with relevant Indian standards [18].

III. OBSERVATIONS AND RESULT

The results indicate that the variation of compressive strength of the concrete with various different mix samples. Compressive strength of the concrete is maximum in 4% of steel fiber reinforcement with 25 % of fly ash replace with cement and there is a slight decrease in 2% steel fiber reinforcement with 25 % of fly ash. The flexural strength of the concrete is maximum in 4% fiber reinforcement and there is a slight decrease in 2% fiber sample. The variation of strengths of the concrete with partial replacement of fly ash with different % of fiber is shown in figure 6.1.



(a)



(b)

Fig. 1(a) & (b): The variation of strengths of the concrete with partial replacement of fly ash

IV. CONCLUSION

From the above points it can be concluded that fiber reinforcement is very effective for improving the strength characteristics, cracking and workability of the concrete.

Therefore the performance of the concrete will be improved if proper design and construction methodology is adopted.

The maximum compressive strength of specimen after 28 days is 46.44 N/mm² with 4% of hybrid fibers (polypropylene and steel) with 25% of fly ash with comparisons of normal concrete and other mix. It is 20.34 % increase overcome with normal concrete.

The maximum compressive strength of specimen after 28 days is 45.93 N/mm² with 4% of hybrid fibers (polypropylene and steel) with 30% of fly ash with comparisons of normal concrete and other mix. It is 19.02 % increase overcome with normal concrete.

REFERENCES

- [1]. R.H. Mohankar, M.D. Pidurkar, P.V Thakre, S.S. Pakhare (2016); HYBRID FIBRE REINFORCED CONCRETE. IJSETR Volume 5, Issue 1.
- [2]. M VADIVEL, R VENKATASUBRAMANI (2016); Robustness Study of Hybrid Fiber Reinforced Concrete with Steel and Synthetic Fiber. IJESE ISSN 0974-5904, Volume 09, No. 03 June 2016, P.P.575-578.
- [3]. S. Eswari (2015); Experimental Investigation on Flexural Performance of Hybrid Fiber Reinforced Concrete. ISSN: 2395 -0056 Volume: 02 Issue: 03.
- [4]. M. Tamil Selvi1, Dr. T.S. Thandavamoorthy (2013); Studies on the Properties of Steel and Polypropylene Fibre Reinforced Concrete without any Admixture. IJEIT ISSN: 2277-3754 Volume 3, Issue 1, 411.
- [5]. Rajarajeshwari B Vibhuti, Radhakrishna, Aravind N (2013); Mechanical Properties of Hybrid Fiber Reinforced Concrete for Pavements. Ijret ISSN: 2319-7308 244 IC-RICE Conference Issue.
- [6]. Syal Tarun, Goel Sanjay, Bhutani Manish (2013); Compressive Strength of Steel Polypropylene Hybrid Fibre Reinforced Self-Compacting Concrete. ISETT ISSN No. 2250-3641 Vol. 6, Issue 1(Version 6), pp.32-36.
- [7]. Mogre, Dr. Dhananjay K. Parbat (2012); Behaviour of Polypropylene Fibre Reinforce Concrete with Artificial Sand. IRJES ISSN 2319-1821 Volume 1, Issue 2 (October 2012), PP.37-40.
- [8]. S. C. Patodi, C. V. Kulkarni (2012); Performance Evaluation of Hybrid Fiber Reinforced Concrete Matrix. IJERA ISSN: 2248-9622 Vol. 2, Issue5, pp.1856-1863.
- [9]. Vikrant S. Vairagade, Kavita S. Kene (2012); Experimental Investigation on Hybrid Fiber Reinforced Concrete. IJERA ISSN: 2248-9622 Vol. 2, Issue 3, pp.1037-1041 1037.
- [10]. A. Sivakumar (2011); Influence of hybrid fibers on the post crack performance of high strength concrete: Part I experimental investigations. JCECT ISSN 2141-2634 Vol. 2(7),pp. 147-159.
- [11] IS: 10262-2009, "Recommended guidelines for concrete mix design", BIS New Delhi.

- [12] IS: 1199-1959, "Methods of Sampling and Analysis of Concrete", BIS New Delhi.
- [13] IS: 2720 (Part 2)-1973, "Determination of Water Content", BIS New Delhi.
- [14] IS: 2720 (Part 3/Sec 1)-1980, "Determination of Specific gravity", BIS New Delhi.
- [15] IS: 383-1970, "Specification for coarse and fine aggregate from natural sources of concrete", BIS New Delhi.
- [16] IS: 456-2000, "Practice for plain and reinforced concrete", BIS New Delhi.
- [17] IS: 516-1959, "Methods of tests for strength of concrete", BIS New Delhi.
- [18] IS: 8112-1989, "Specifications for 43-Grade Portland cement", BIS New Delhi.